

SECTION 1043 AGGREGATE FROM CRUSHED CONCRETE

1043-1 GENERAL

Aggregate from crushed concrete is a recycled product made by crushing concrete obtained from concrete truck clean out, demolition of existing concrete structures or pavement, or similar sources and transported from a crushing facility. It does not include concrete pavements that are rubblelized, broken or otherwise crushed in place on the roadway.

The crushed material must meet all sources approval requirements described in Sections 1005 and 1006 with the exception of the sodium sulfate test requirement. Deleterious materials shall not be more than 3%.

Sampling and acceptance for the determination of gradation, LL and PI will be performed as described in the *Aggregate QC/QA Program Manual* and the *Aggregate Sampling Manual*.

1043-2 AGGREGATE BASE COURSE

The material shall meet the ABC gradation. The LL of the material shall be raised 5 points to no more than 35.

1043-3 AGGREGATE SHOULDER BORROW

The material shall meet Section 1019.

1043-4 CLEAN COARSE AGGREGATE FOR ASPHALT

The material shall meet the gradation of a standard size in Table 1005-1. Use of the material shall be approved by the Engineer, and the mix shall meet all requirements.

1043-5 CLEAN COARSE AGGREGATE FOR CONCRETE

The material shall meet the gradation of a standard size in Table 1005-1. Use of the material is restricted to Class B concrete mixes only. Use of the material shall be approved by the Engineer, and the concrete shall meet all requirements.