

**TABLE 1005-2
AGGREGATE GRADATION FINE AGGREGATE**

Std. Size #	Percentage of Total by Weight Passing								Remarks
	3/8"	#4	#8	#16	#30	#50	#100	#200	
1S	100	90-100		40-85		0-20		0-3	Blotting Sand, Asphalt Retreatment
2S	100	95-100	80-100	45-95	25-75	5-30	0-10	0-3	Concrete, Shotcrete, Grout, Subsurface Drainage, Blotting Sand
2MS		95-100	80-100	45-95	25-75	5-35	0-20	0-8 ^A	Concrete, Shotcrete, Grout, Subsurface Drainage
4S		100	95-100			15-45	0-10	0-5	Mortar

A. When tested at the job site before use, the amount of material passing the No. 200 sieve shall not be greater than 10%.