

**TABLE 1012-5
LIGHTWEIGHT AGGREGATE PHYSICAL PROPERTIES**

| Property | Specification (maximum limit) | Test Method |
|--------------------------|--|-------------------------|
| Sodium Sulfate Soundness | 5% | AASHTO T 104 |
| Los Angeles Abrasion | 45% | AASHTO T 96 (B grading) |
| Percent Absorption | 10% | AASHTO T 19 |
| Micro-Deval | 18% | AASHTO T 327 |